

Technical Bulletin

JEFFAMINE® T-403 Polyetheramine

JEFFAMINE T-403 polyetheramine is is characterized by repeating oxypropylene units in the backbone. As shown by the structure, JEFFAMINE T-403 is a trifunctional primary amine having an average molecular weight of approximately 440. Its amine groups are located on secondary carbon atoms at the ends of aliphatic polyether chains.

APPLICATIONS

- Epoxy curing agent
- · Anti-sag agent for polyurethanes

BENEFITS

- Low color and vapor pressure
- Completely miscible with a wide variety of solvents, including water
- · Improves flexibility and strength

SALES SPECIFICATIONS

Property	Specifications	Test Method*
Appearance	Colorless to pale yellow with slight haze	ST-30.1
Color, Pt-Co	50 max.	ST-30.12
Primary amine, % of total amine	90 min.	ST-5.34
Total acetylatables, meq/g	6.5 min. – 7.1 max.	ST-31.39
Total amine, meq/g	6.1 min. – 6.6 max.	ST-5.35
Water, wt%	0.25 max.	ST-31.53, 6

*Methods of Test are available from Huntsman Corporation upon request.

ADDITIONAL INFORMATION

Listed

Regulatory Information

China, IECSC

DOT/TDG Classification Corrosive liquids, toxic, N.O.S. (polyoxypropylenetriamine) **HMIS Code** 3-1-0 **CAS Number** 39423-51-3 US. TSCA Listed Canadian WHMIS Classification D1B, E Canada, DSL Listed European Union, EINECS/ELINCS Polymer Exempt Australia, AICS Listed Japan, ENCS Contact Huntsman Regulatory Korea, ECL Listed

Typical Physical Properties

AHEW (amine hydrogen equiva	alent wt.), g/eq 81
Viscosity, cSt, 25°C (77°F)	72
Density, g/ml (lb/gal), 25°C	0.978 (8.12)
Flash point, PMCC, °C (°F)	196 (385)
pH, 5% aqueous solution	11.6
Refractive index, n _D ²⁰	1.46
Vapor Pressure, mmHg/°C	1/181
•	5/207



TOXICITY AND SAFETY

For additional information on the toxicity and safe handling of this product, consult the Material Safety Data Sheet (Safety Data Sheet in Europe) prior to use of this product.

HANDLING AND STORAGE

Materials of Construction

At temperatures of 75-100°F (34-38°C)

Tanks Carbon steel Lines, valves Carbon steel **Pumps** Carbon steel Heat exchange Surfaces Stainless steel

Hoses

Stainless steel, polyethylene, polypropylene, and $\mathsf{TEFLON}^{\mathbb{B}}$ Polypropylene or $\mathsf{TEFLON}^{\mathbb{B}}$ (elastomers such as neoprene, Buna N, and Gaskets, packing

VITON® should be avoided)

Atmosphere Nitrogen or dry air

At temperatures above 100°F (38°C)

Tanks Stainless steel or aluminum

Lines, Valves Stainless steel

Pumps Stainless steel or Carpenter 20 equivalent

Atmosphere Nitrogen

JEFFAMINE® T-403 polyetheramine may be stored under air at ambient temperatures for extended periods. A nitrogen blanket is suggested for all storage, however, to reduce the effect of accidental exposure to high temperatures and to reduce the absorption of atmospheric moisture and carbon dioxide. It should be noted that pronounced discoloration is likely to occur at temperatures above 140°F (60°C), whatever the gaseous pad.

Cleanout of lines and equipment containing JEFFAMINE T-403 polyetheramine can be accomplished using warm water and steam. In the event of spillage of this product, the area may be flushed with water. The proper method for disposal of waste material is by incineration with strict observance of all federal, state, and local regulations.

AVAILABILITY

JEFFAMINE T-430 polyetheramine is available in tank cars, tank wagons, 55-gallon (208L) drums of 440 pounds (200kg) net weight, and 5-gallon (19L) cans. Samples are available in North America and Asia by contacting our sample department at 1-800-662-0924. Samples in other locations, including Europe, are available by contacting any Huntsman Corporation sales office.

5209-0208

Copyright © 2007, 2008 Huntsman Corporation or an affiliate thereof. All rights reserved.

JEFFAMINE® is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries

VITON® and TEFLON® are registered trademarks of Dupont.

Huntsman Petrochemical Corporation warrants only that its products meet the specifications stated in the sales contract. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on these products, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPHIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE MERCHANTABILITY OR SUITABILITY OR INTENSES OF ANY CHEMICAL COMPOUNDS FOR ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT.

EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. Liability of Huntsman Petrochemical Corporation and its affiliates for all claims is limited to the purchase price of the material. Products may be toxic and require special precautions in handling. For all products listed, user should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

Main Offices US: Huntsman Corporation / 10003 Woodloch Forest Drive / The Woodlands, Texas 77380 / 281-719-6000 Technical Service US: 8600 Gosling Road / The Woodlands, Texas 77381 / 281-719-7780

Main Offices Europe: Huntsman Belgium BVBA / Everslaan 45 / B-3078 Everberg, Belgium / 32-2 -758-9211

Main Offices Asia Pacific: Huntsman Singapore PTE / 150 Beach Road #37-00 Gateway West / Singapore 189720 / 65 6297 3363
Technical Service Asia Pacific: Huntsman Performance Products / 61 Market Road, Brooklyn, Victoria / Australia 3012 / 61 3 9933 6666